

Product description:

KICRO5 ISM CR 30 is a chloroprene compound crafted with balanced properties of major rubbers and provides excellent adhesion to metals. The compound is known for its excellent tackiness and wide general purpose uses.

Chemistry:

The compound is technically homopolymer of 2-chloro 1, 3-butadiene with trans 1, 4 units around 90% which accounts to synthetic rubber with crystallization as inherent property.

Properties:

The compound covers wider properties including ozone and oxidation stability, low flammability and moderate oil resistance than most of the general purpose synthetics.

Service temperature:

-35°C to 100°C.

Product ranges:

Gasket, Bellows.

Physical properties:

S.No	Description	ASTM Standard	Units	Specification
I	Hardness	D2240	Shore A	30 ± 5
II	Tensile Strength (Min)	D412	MPa	10
III	Modulus @ 100 % (Min.)	D412	MPa	0.4
III	Elongation (Min)	D412	%	500
IV	Compression Set (Max) (22 hrs @ 100°C) Compression Set (Max) (70 hrs @ 100°C)	D395 Method B	%	35 50
V	Heat Ageing 70 hrs @ 100°C Hardness Change Tensile Change(Max) Elongation Change(Max)	D573	Shore A % %	+ 15 - 15 - 40
VI	ASTM : 1 Oil Ageing 70 hrs @ 100°C Hardness Change Tensile Change (Max) Elongation Change(Max) Volume Swelling (Max)	D471	Shore A % % %	± 10 - 30 - 30 - 15 to + 15
VII	ASTM : 3 Oil Ageing 70 hrs @ 100°C Hardness Change Tensile Change (Max) Elongation Change(Max) Volume Swelling (Max)	D471	Shore A % % %	- 30 - 70 - 55 + 120

NOTE: The Above Compound Meets As Per ASTM D2000 M2 BC 310 A14 B14 E014 E034

The technical datasheets are derived on the basis of the service conditions and end user preference in which the values derived are given over a range of specifications which are cross checked over a variety of trials and approved with the end user conditions and calculated over a prolonged time



Industrial Spares Manufacturing and Trading Co.
No 66 & 77, Perungudi industrial estate,
Perungudi, Chennai – 600096
Tamilnadu, India
Ph: 24961147